



*West Yorkshire  
Materials Testing  
Service*

PO Box 5, Morley, LS27 0QP Page 1 of 1  
Nepshaw Lane South, Morley, Leeds  
Tel 0113 253 0241 Fax 0113 252 7029  
Head of Laboratory **G. Briggs C. Text ATI**

**Client:**

KBT LTD  
132 Salfley Road  
Birmingham B7 4TH  
T 350 1836 F 0870 350 1938

**Entry No:** 39763  
**Date received:** 07/10/2009

**Client's Description:** Sample of fabric Ref: 6905, Venus, 100% polyester

**TEST REPORT**

**Test Required:** Flammability BS 5867-2 : Type B  
**Pre-treatment:** None  
**Conditioning:** A minimum of 24 hours at 65 +/- 5% Relative Humidity, 20 +/- 2°C  
**Method of Test:** BS EN ISO 15025 : 2002 Procedure A (surface ignition)  
**Date of Test:** 14/10/2009

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

**Flame application time 15 seconds using propane gas**

No part of any hole or the lowest boundary of any flame reached the upper edge or either vertical edge on any specimen. There was no separation of flaming debris from any specimen.

**Comments**

On the basis of the tests carried out this sample of fabric meets the Type B requirements of BS 5867-2 : 2008.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



*G Briggs*

G Briggs  
Head of Laboratory  
15<sup>th</sup> October 2009

- ◆ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ◆ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ◆ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ◆ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

