



## TEST REPORT

**Entry No:** 84141-01  
**Date received:** 04/05/2017  
**Client's Description:** Sample of fabric: KBT14149, woven screen fabric, colour Purple Drift  
**Test Required:** Flammability BS 5867-2: Type B  
**Pre-treatment:** None  
**Conditioning:** A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C  
**Date Tests Completed:** 11/05/2017  
**Method of Test:** BS EN ISO 15025: 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

### Flame application time 15 seconds using propane gas

| Face of Fabric tested          | Fabric length direction |    |    | Fabric width direction |    |    |
|--------------------------------|-------------------------|----|----|------------------------|----|----|
| Specimen number                | 1↑                      | 2↓ | 3↑ | 4→                     | 5← | 6→ |
| Flame reached an edge (✓ or X) | X                       | X  | X  | X                      | X  | X  |
| Hole reached an edge (✓ or X)  | X                       | X  | X  | X                      | X  | X  |
| Flaming debris (✓ or X)        | X                       | X  | X  | X                      | X  | X  |

### Comments

On the basis of the tests carried out this sample of fabric meets the Type B requirements of BS 5867-2: 2008.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein*



Dale Brockbank  
 Materials Testing Manager  
 Date of original 11 May 2017  
 Date of amendment 12 May 2017

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
  - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
  - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

